

In The Specification

Please replace the paragraph beginning on page 5, line 7 with the following amended paragraph:

At most 30 mole% of organic monomers, such as cyclohexyl vinyl ether, 4-hydroxybutyl vinyl ether, ethyl vinyl ether, methyl methacrylate, butyl acrylate, 4-hydroxyethyl methacrylamide, glyceryl methacrylamide, acrolein, butyl vinyl ether, propionic vinyl ether, α,α -dimethylpropionic vinyl ether, or combinations thereof, can be added to the polymer comprising compounds other than perfluorinated polymer of the present invention when and copolymerized with VdF and other monomers such as HFP, CTFE, TFE, or combinations thereof in order to further enhance the solubility and adhesion with the substrate of the electret without negative affect on the polarized initial surface potential and charge stability thereof.